


# アルミ・ステンリベット

リベット部材質：アルミニウム(A-5154)

シャフト部材質：ステンレス(SUS304相当品)

丸頭



リベット径 (D) φ mm	下穴径 φ mm	品番	適正カシメ板厚 mm	リベット長さ (L) mm	フランジ厚 (P) mm	フランジ径 (A) φ mm	引張強度 N	剪断強度 N
2.4	2.5	AC-32AS	1.0~3.2	5.6	0.9	4.8	730	490
	↘	AC-33AS	1.6~4.8	7.6				
	2.6	AC-34AS	3.2~6.4	9.1				
3.2	3.3 ↘ 3.4	AC-41AS	1.0~1.6	4.8	1.1	6.4	1420	930
		AC-42AS	1.6~3.2	6.5				
		AC-43AS	3.2~4.8	8.2				
		AC-44AS	4.8~6.4	9.9				
		AC-45AS	6.4~7.9	11.6				
		AC-46AS	7.9~9.5	13.3				
		AC-48AS	9.5~12.7	16.7				
		AC-410AS	12.7~15.9	19.0				
		AC-412AS	15.9~19.1	23.0			1340	870
4.0	4.1 ↘ 4.2	AC-52AS	1.2~3.2	7.2	1.3	8.0	2250	1470
		AC-53AS	3.2~4.8	8.9				
		AC-54AS	4.8~6.4	10.5				
		AC-55AS	6.4~7.9	12.2				
		AC-56AS	7.9~9.5	13.9				
		AC-58AS	9.5~12.7	17.2				
		AC-510AS	12.7~15.9	19.7				
		AC-512AS	15.9~19.1	23.0				
4.8	4.9 ↘ 5.0	AC-62AS	1.6~3.2	7.6	1.9	9.6	3250	2150
		AC-63AS	3.2~4.8	9.3				
		AC-64AS	4.8~6.4	11.0				
		AC-65AS	6.4~7.9	12.8				
		AC-66AS	7.9~9.5	14.5				
		AC-68AS	9.5~12.7	17.9				
		AC-610AS	12.7~15.9	21.3				
		AC-612AS	15.9~19.1	23.3				
		AC-614AS	19.1~22.2	26.5				
		AC-616AS	22.2~25.4	29.7				
6.4	6.5 ↘ 6.6	AC-82AS	1.6~3.2	9.2	2.4	12.8	5390	3350
		AC-84AS	3.2~6.4	12.4				
		AC-86AS	6.4~9.5	15.6				
		AC-88AS	9.5~12.7	18.9				
		AC-810AS	12.7~15.9	22.1				
		AC-812AS	15.9~19.1	25.4				
		AC-814AS	19.1~22.2	28.6				



アブデルック株式会社

〒224-0003 横浜市都筑区中川中央1-4-6 フォーレスト・センタービル 3F

TEL 045-532-6900 FAX 045-532-6909

<http://www.avdelook.co.jp>