


オープンタイプ(オール鉄) リベット

リベット部材質: **スチール**(炭素鋼)

シャフト部材質: **スチール**(高炭素鋼)

丸頭



リベット径 (D) φ mm	下穴径 φ mm	品番	適正カシメ板厚 mm	リベット長さ (L) mm	フランジ厚 (P) mm	フランジ径 (A) φ mm	引張強度 N	剪断強度 N
2.4	2.5 ↙ 2.6	※AC-32T	1.0~3.2	5.5	0.8	4.8	930	680
		※AC-34T	3.2~6.4	8.7				
3.2	3.3 ↙ 3.4	AC-41T	1.0~1.6	4.8	1.1	6.4	1670	1200
		AC-42T	1.6~3.2	6.4				
		AC-43T	3.2~4.8	8.0				
		AC-44T	4.8~6.4	9.5				
		AC-45T	6.4~7.9	11.2				
		AC-46T	7.9~9.5	12.7				
4.0	4.1 ↙ 4.2	AC-48T	9.5~12.7	15.9	1.3	8.0	2500	1900
		AC-52T	1.2~3.2	7.0				
		AC-53T	3.2~4.8	8.6				
		AC-54T	4.8~6.4	10.2				
		AC-55T	6.4~7.9	11.8				
		AC-56T	7.9~9.5	13.3				
4.8	4.9 ↙ 5.0	AC-58T	9.5~12.7	16.5	1.8	9.6	3630	2700
		AC-62T	1.6~3.2	7.6				
		AC-63T	3.2~4.8	9.2				
		AC-64T	4.8~6.4	10.8	1.3	9.5	6500	4400
		AC-65T	6.4~7.9	12.4				
		AC-66T	7.9~9.5	14.0				
		AC-68T	9.5~12.7	17.2	2.4	12.8	6500	4400
		AC-610T	12.7~15.9	20.4				
		AC-612T	15.9~19.1	23.6				
6.4	6.5 ↙ 6.6	AC-614T	19.1~22.2	26.5	2.4	12.8	6500	4400
		AC-616T	22.2~25.4	29.7				
		AC-84T	3.2~6.4	12.4				
		AC-86T	6.4~9.5	15.6				
		AC-88T	9.5~12.7	18.9				
		AC-810T	12.7~15.9	22.1				
AC-812T	15.9~19.1	25.4	28.6					
AC-814T	19.1~22.2	28.6						

注) ※印のリベット部の材質は、SPCCになります。



アデルック 株式会社

〒224-0003 横浜市都筑区中川中央1-4-6 フォーレスト・センタービル 3F

TEL 045-532-6900 FAX 045-532-6909

<http://www.avdelook.co.jp>