


オールアルミリベット

リベット部材質：アルミニウム(A-5052)

シャフト部材質：アルミニウム(A-2017)

丸頭



リベット径 (D) φ mm	下穴径 φ mm	品番	適正カシメ板厚 mm	リベット長さ (L) mm	フランジ厚 (P) mm	フランジ径 (A) φ mm	引張強度 N	剪断強度 N
2.4	2.5	※AC-32A	1.0~3.2	5.6	0.9	4.8	620	417
	2.6	※AC-33A	1.6~4.8	7.6				
		※AC-34A	3.2~6.4	9.1				
3.2	3.3 3.4	AC-41A	1.0~1.6	4.8	1.1	6.4	1030	690
		AC-42A	1.6~3.2	6.5				
		AC-43A	3.2~4.8	8.2				
		AC-44A	4.8~6.4	9.9				
		AC-45A	6.4~7.9	11.6				
		AC-46A	7.9~9.5	13.3				
		AC-48A	9.5~12.7	16.7				
		AC-410A	12.7~15.9	19.0				
4.0	4.1 4.2	AC-52A	1.2~3.2	7.2	1.3	8.0	1570	1100
		AC-53A	3.2~4.8	8.9				
		AC-54A	4.8~6.4	10.5				
		AC-55A	6.4~7.9	12.2				
		AC-56A	7.9~9.5	13.9				
		AC-58A	9.5~12.7	17.2				
		AC-510A	12.7~15.9	19.7				
4.8	4.9 5.0	AC-62A	1.6~3.2	7.6	1.9	9.6	2250	1550
		AC-63A	3.2~4.8	9.3				
		AC-64A	4.8~6.4	11.0				
		AC-65A	6.4~7.9	12.8				
		AC-66A	7.9~9.5	14.5				
		AC-68A	9.5~12.7	17.9				
		AC-610A	12.7~15.9	21.3				
		AC-612A	15.9~19.1	24.8				
		AC-614A	19.1~22.2	28.2				
6.4	6.5 6.6	AC-82A	1.6~3.2	9.2	2.4	12.8	4100	2500
		AC-84A	3.2~6.4	12.4				
		AC-86A	6.4~9.5	15.6				
		AC-88A	9.5~12.7	18.9				
		AC-810A	12.7~15.9	22.1				
		AC-812A	15.9~19.1	25.4				
		AC-814A	19.1~22.2	28.6				

注) ※印のシャフト部の材質は、アルミニウム(A-5014)になります。



アブデルック株式会社

〒224-0003 横浜市都筑区中川中央1-4-6 フォーレスト・センタービル 3F

TEL 045-532-6900 FAX 045-532-6909

<http://www.avdelook.co.jp>