


オープンタイプ リベット

リベット部材質： アルミニウム(A-5154)

シャフト部材質： スチール(炭素鋼)

皿頭



リベット径 (D) φ mm	下穴径 φ mm	品番	適正カシメ板厚 mm	リベット長さ (L) mm	フランジ厚 (P) mm	フランジ径 (A) φ mm	引張強度 N	剪断強度 N		
2.4	2.5	AC-32K	1.0~3.2	5.6	0.8	4.8	630	490		
	↷	AC-33K	1.6~4.8	7.6						
	2.6	AC-34K	3.2~6.4	9.1						
3.2	3.3 ↷ 3.4	AC-42K	1.6~3.2	6.5	1.2	6.4	1200	930		
		AC-43K	3.2~4.8	8.2						
		AC-44K	4.8~6.4	9.9						
		AC-45K	6.4~7.9	11.6						
		AC-46K	7.9~9.5	13.3						
		AC-48K	9.5~12.7	16.7						
		※AC-410K	12.7~15.9	19.0					1340	870
	※AC-412K	15.9~19.1	23.0							
4.0	4.1 ↷ 4.2	AC-52K	1.2~3.2	7.2	1.5	8.0	2100	1470		
		AC-53K	3.2~4.8	8.9						
		AC-54K	4.8~6.4	10.5						
		AC-55K	6.4~7.9	12.2						
		AC-56K	7.9~9.5	13.9						
		AC-58K	9.5~12.7	17.2						
		※AC-510K	12.7~15.9	19.7						
		※AC-512K	15.9~19.1	23.0						
4.8	4.9 ↷ 5.0	AC-62K	1.6~3.2	7.6	1.7	9.6	3100	2250		
		AC-63K	3.2~4.8	9.3						
		AC-64K	4.8~6.4	11.0						
		AC-65K	6.4~7.9	12.8						
		AC-66K	7.9~9.5	14.5						
		AC-68K	9.5~12.7	17.9						
		AC-610K	12.7~15.9	21.3						
		※AC-612K	15.9~19.1	23.3						
		※AC-614K	19.1~22.2	26.5						
6.4	6.5 ↷ 6.6	※AC-82K	1.6~3.2	9.2	1.9	12.8	5390	3350		
		※AC-84K	3.2~6.4	12.4						
		※AC-86K	6.4~9.5	15.6						
		※AC-88K	9.5~12.7	18.9						
		※AC-810K	12.7~15.9	22.1						
		※AC-812K	15.9~19.1	25.4						
		※AC-814K	19.1~22.2	28.6						

注) ※印のリベットは受注生産になりますので、納期はご相談下さい。



アブデルック 株式会社

〒224-0003 横浜市都筑区中川中央 1-4-6 フォーレスト・センタービル 3F

TEL 045-532-6900 FAX 045-532-6909

<https://www.avdelook.co.jp>